



2079 Center Square Road
Logan Township, NJ 08085

TECHNICAL DATA AND PROCESS SHEET

PERMANENTLY ANTISTATIC ABS

INELEC ABSAS

TYPICAL PROPERTIES

<u>PROPERTY</u>	<u>VALUE</u>	<u>UNIT</u>	<u>METHOD</u>
PHYSICAL			
SPECIFIC GRAVITY	1.07	-	ASTM D792
MOLD SHRINKAGE, FLOW 0.125"	0.5-0.7	%	ASTM D955
MECHANICAL			
TENSILE STRENGTH, YLD	6,000	psi	ASTM D638
TENSILE ELONGATION, YLD	>10%	%	ASTM D638
FLEXURAL MODULUS	300,000	psi	ASTM D790
IZOD IMPACT, NOTCHED	3.8	ft-lb/in	ASTM D256
IZOD IMPACT, UNNOTCHED	NB	ft-lb/in	ASTM D4812
THERMAL			
HDTUL @ 264 PSI	170	°F	ASTM D648
ELECTRICAL			
SURFACE RESISTIVITY	1E9-1E11	Ohms/sq	ASTM D257
PROCESSING			
DRYING TEMPERATURE	180	°F	
DRYING TIME	3-4	hrs	
MAX MOISTURE CONTENT	0.075	%	
MELT TEMPERATURE	460-490	°F	
MOLD TEMPERATURE	180	°F	
BACK PRESSURE	50-100	psi	
SCREW SPEED	40-70	rpm	
VENT DEPTH	0.0015-0.003	in	

Revised 11/3/10 DJV

This information is based on our experience to date and we believe it to be reliable. It is intended only as a guide for use at your discretion and risk. We cannot guarantee favorable results and assume no liability in connection with its use of the products described. Each user bears full responsibility for making it's own determination as to the suitability of the product described. None of this information is to be taken as a license to operate under, or recommendation to infringe any patents