



2079 Center Square Road  
Logan Township, NJ 08085

**TECHNICAL DATA AND PROCESS SHEET**

---

**15% PTFE LUBRICATED POLYCARBONATE/ABS ALLOY**

**INLUBE PCABSTF15**

**TYPICAL PROPERTIES**

<b>PROPERTY</b>	<b>VALUE</b>	<b>UNIT</b>	<b>METHOD</b>
<b>PHYSICAL</b>			
SPECIFIC GRAVITY	1.20	-	ASTM D792
MOLD SHRINKAGE, FLOW 0.125"	0.5-0.7	%	
<b>MECHANICAL</b>			
TENSILE STRENGTH, BRK	6700	psi	ASTM D638
TENSILE ELONGATION	10-20	%	ASTM D638
FLEXURAL MODULUS	330,000	psi	ASTM D790
IZOD IMPACT, NOTCHED	3.50	ft-lb/in	ASTM D256
<b>THERMAL</b>			
HDTUL @ 264 PSI	270	°F	ASTM D648
<b>ELECTRICAL</b>			
VOLUME RESISTIVITY	>1exp17	Ohm-cm	ASTM D257
<b>PROCESSING</b>			
DRYING TEMPERATURE	200	°F	
DRYING TIME	3-4	hrs	
MAX MOISTURE CONTENT	0.02	%	
MELT TEMPERATURE	475-520	°F	
MOLD TEMPERATURE	140-180	°F	
BACK PRESSURE	50-100	psi	
SCREW SPEED	40-70	rpm	
VENT DEPTH	0.001-0.002	in	

Revised TSC 11/20/09

This information is based on our experience to date and we believe it to be reliable. It is intended only as a guide for use at your discretion and risk. We cannot guarantee favorable results and assume no liability in connection with its use of the products described. Each user bears full responsibility for making it's own determination as to the suitability of the product described. None of this information is to be taken as a license to operate under, or recommendation to infringe any patents