



2079 Center Square Road
 Logan Township, NJ 08085
 Phone: 856-467-3030

TECHNICAL DATA AND PROCESS SHEET

**30% CARBON FIBER REINFORCED 15% PTFE LUBRICATED COPOLYMER ACETAL
 INLUBE POMCCF30TF15**

TYPICAL PROPERTIES

PROPERTY	ASTM METHOD	English	UNITS	Metric SI	UNITS
GENERAL					
SPECIFIC GRAVITY	D792	1.58		1.58	
SPECIFIC VOLUME		17.5	in ³ /lb	0.633	cm ³ /gm
WATER ABSORPTION (24 Hrs)	D570	0.5	%	0.50	%
MOLD SHRINKAGE	D955	0.4-0.6	%	0.4-0.6	%
MECHANICAL					
TENSILE STRENGTH	D638	21,500	psi	148	MPa
ELONGATION, YIELD	D638	1-2	%	1-2	%
FLEXURAL STRENGTH	D790	34,000	psi	234	MPa
FLEXURAL MODULUS	D790	2,100,000	psi	14,479	MPa
SHEAR STRENGTH	D732				
IZOD IMPACT STRENGTH	D256				
NOTCHED 1/8"		1.0	ft.lb./in.	53	J/m
UNNOTCHED 1/8"		4	ft.lb./in.	213	J/m
ROCKWELL HARDNESS					
THERMAL					
HDTUL @ 264 PSI	D648	325	°F	163	°C
COEFFICIENT OF LINEAR THERMAL EXPANSION	D696	2	in./in. F x10 ⁻⁵	3.6	mm/mm C 10 ⁻⁶
FLAMMABILITY ¹	U.L.Subj 94	HB@1/16	in	HB@1.5	mm
ELECTRICAL					
SURFACE RESISTIVITY		10e ² -10e ⁶	ohms/sq	10e ² -10e ⁶	ohms/sq
PROCESSING					
DRYING TEMPERATURE		180	°F	82	°C
DRYING TIME		4	hrs	4	hrs
MELT TEMPERATURE		375-410	°F	190 - 210	°C
MOLD TEMPERATURE		200	°F	93	°C
BACK PRESSURE		50-100	psi	0.3 - 0.7	MPa
SCREW SPEED		30-60	rpm	30-60	rpm
VENT DEPTH		0.0005-0.001	in	0.0125 - 0.0251	mm

This information is based on our experience to date and we believe it to be reliable. It is intended only as a guide for use at your discretion and risk. We cannot guarantee favorable results and assume no liability in connection with its use of the products described. Each user bears full responsibility for making it's own determination as to the suitability of the product described. None of this information is to be taken as a license to operate under, or recommendation to infringe any patents