



2079 Center Square Road
 Logan Township, NJ 08085
 856-467-3030 Phone

TECHNICAL DATA AND PROCESS SHEET

20% PTFE LUBRICATED ACETAL HOMOPOLYMER

INLUBE POMHTF20

TYPICAL PROPERTIES

PROPERTY	VALUE	UNIT	METHOD
PHYSICAL			
SPECIFIC GRAVITY	1.53	-	ASTM D792
WATER ABSORPTION	0.2	%	ASTM D570
MOLD SHRINKAGE, FLOW 0.125"	1.8-2.3	%	ASTM D955
MECHANICAL			
TENSILE STRENGTH, BRK	7,700	psi	ASTM D638
TENSILE ELONGATION (BRK)	10-15	%	ASTM D638
FLEXURAL MODULUS	380,000	psi	ASTM D790
IZOD IMPACT, NOTCHED	0.9	ft-lb/in	ASTM D256
IZOD IMPACT, UNNOTCHED	10-12	ft-lb/in	ASTM D4812
THERMAL			
HDTUL @ 264 PSI	204	°F	ASTM D648
ELECTRICAL			
SURFACE RESISTIVITY	>10 ¹⁷	Ohm/Sq	ASTM D257
PROCESSING			
DRYING TEMPERATURE	180	°F	
DRYING TIME	4	hrs	
MELT TEMPERATURE	390-410	°F	
MOLD TEMPERATURE	180-220	°F	
BACK PRESSURE	25-50	psi	
SCREW SPEED	30-60	rpm	
VENT DEPTH	0.0005-0.001	in	

REVISED: 1/11/11 DJV

This information is based on our experience to date and we believe it to be reliable. It is intended only as a guide for use at your discretion and risk. We cannot guarantee favorable results and assume no liability in connection with its use of the products described. Each user bears full responsibility for making it's own determination as to the suitability of the product described. None of this information is to be taken as a license to operate under, or recommendation to infringe any patents