



2079 Center Square Road
Logan Township, NJ 08085

TECHNICAL DATA AND PROCESS SHEET

30% GLASS FIBER REINFORCED NYLON 6/12

INSTRUC PA612GF30

TYPICAL PROPERTIES

<u>PROPERTY</u>	<u>VALUE</u>	<u>UNIT</u>	<u>METHOD</u>
PHYSICAL			
SPECIFIC GRAVITY	1.30	-	ASTM D792
WATER ABSORPTION	0.2	%	ASTM D570
MOLD SHRINKAGE, FLOW 0.125"	0.3 - 0.5	%	ASTM D955
MECHANICAL			
TENSILE STRENGTH, BRK	27,000	psi	ASTM D638
TENSILE ELONGATION	2-4	%	ASTM D638
TENSILE MODULUS	1,300,000	psi	ASTM D638
FLEXURAL STRENGTH	35,000	psi	ASTM D790
FLEXURAL MODULUS	1,200,000	psi	ASTM D790
IZOD IMPACT, NOTCHED	2.5	ft-lb/in	ASTM D256
IZOD IMPACT, UNNOTCHED	22	ft-lb/in	ASTM D4812
THERMAL			
HDTUL @ 264 PSI	425	°F	ASTM D648
FLAMMABILITY	HB @ 1.5 mm		
ELECTRICAL			
SURFACE RESISTIVITY	$>10^{17}$	Ohm/Sq	ASTM D257
PROCESSING			
DRYING TEMPERATURE	175	°F	
DRYING TIME	4	hrs	
MELT TEMPERATURE	510-530	°F	
MOLD TEMPERATURE	200	°F	
BACK PRESSURE	50-100	psi	
SCREW SPEED	40-70	rpm	
VENT DEPTH	0.0005-0.001	in	

Revised: 12/8/10 DJV

This information is based on our experience to date and we believe it to be reliable. It is intended only as a guide for use at your discretion and risk. We cannot guarantee favorable results and assume no liability in connection with its use of the products described. Each user bears full responsibility for making it's own determination as to the suitability of the product described. None of this information is to be taken as a license to operate under, or recommendation to infringe any patents