



2079 Center Square Road  
 Logan Township, NJ 08085  
 Phone: 856-467-3030

**TECHNICAL DATA AND PROCESS SHEET**

**20% GLASS FIBER REINFORCED NYLON 6/6**

**INSTRUC PA66GF20**

**TYPICAL PROPERTIES**

PROPERTY	ASTM		UNITS	Metric SI	UNITS
	METHOD	English			
<b>GENERAL</b>					
SPECIFIC GRAVITY	D792	1.28		1.28	
SPECIFIC VOLUME		21.64	in <sup>3</sup> /lb	0.781	cm <sup>3</sup> /gm
WATER ABSORPTION (24 Hrs)	D570	0.90	%	0.90	%
MOLD SHRINKAGE	D955	0.5-0.6	%	0.5-0.6	%
<b>MECHANICAL</b>					
TENSILE STRENGTH	D638	19,000	psi	131	MPa
ELONGATION, YIELD	D638	2-4	%	2-4	%
FLEXURAL STRENGTH	D790	29,000	psi	200	MPa
FLEXURAL MODULUS	D790	1,100,000	psi	7,584	MPa
SHEAR STRENGTH	D732	10,600	psi	73	MPa
IZOD IMPACT STRENGTH	D256				
NOTCHED 1/8"		1.4	ft.lb./in.	75	J/m
UNNOTCHED 1/8"		8.5	ft.lb./in.	453	J/m
ROCKWELL HARDNESS		M93	M Scale	M93	M Scale
<b>THERMAL</b>					
HDTUL	D648	475	°F	246	°C
@ 264 PSI					
COEFFICIENT OF LINEAR THERMAL EXPANSION	D696	2.3	in./in. F x10 <sup>-5</sup>	4.14	mm/mm C 10 <sup>-6</sup>
FLAMMABILITY <sup>1</sup>	U.L.Subj 94	HB@1/16	in	HB@ 1.5	mm
<b>ELECTRICAL</b>					
SURFACE RESISTIVITY		10e <sup>16</sup>	ohms/sq	10e <sup>16</sup>	ohms/sq
<b>PROCESSING</b>					
DRYING TEMPERATURE		175	°F	79	°C
DRYING TIME		4	hrs	4	hrs
MELT TEMPERATURE		500-575	°F	260 - 301	°C
MOLD TEMPERATURE		200	°F	93	°C
BACK PRESSURE		50-100	psi	0.3 - 0.7	MPa
SCREW SPEED		40-70	rpm	40-70	rpm
VENT DEPTH		0.0005-0.001	in	0.0125 - 0.025	mm

This information is based on our experience to date and we believe it to be reliable. It is intended only as a guide for use at your discretion and risk. We cannot guarantee favorable results and assume no liability in connection with its use of the products described. Each user bears full responsibility for making it's own determination as to the suitability of the product described. None of this information is to be taken as a license to operate under, or recommendation to infringe any patents.